

Technical Data Sheet

EZ032

Description: This material is comprised of particulate and fiber fillers blended with enhanced modulus PTFE.

Color: Black

Typical Properties	Test	Value	Units
Specific Gravity	ASTM D-4745	2.05	(-)
Tensile Strength at Break	ASTM D-4745	2000	psi
Elongation at Break	ASTM D-4745	25	%
Hardness	ASTM D2240	58	Shore D
Bulk Density	ASTM D-4745	500	g/l
Service Temperature Range	N/A	-360 to 575	°F
Deformation Under Load	Based on ASTM D-621	2.0 Initial 1.0 Permanent	% (Test Conditions 2000 psi, 70°F)
Deformation Under Load	Based on ASTM D-621	0.8 Initial 0.9 Permanent	% (Test Conditions 600 psi, 500°F)
Compressive Strength	ASTM D-695	3200	psi

Notice:

Technical information, test data and advice provided by Eclipse Engineering are based on information and tests we believe to be reliable and are intended for persons with knowledge and technical skill sufficient to analyze test types and apply adequate safety factors for the given application. Because actual application conditions vary widely, these values are intended for comparative purposes only and the suitability of this material is ultimately left to the end user.